



Product Name MasimoSol GTL GS 250

Region Global

Product Category Synthetic Paraffins

CAS Registry Number 1174918-46-7

EINECS Number 940-728-4

Description

MasimoSol GTL GS 250 is a member of the product range that is derived from Gas-To-liquid (GTL) technology. This technology delivers highly paraffinic products of constant composition. GTL products are typically very low in odour to even odourless. In addition sulphur, olefins, and aromatics levels are very low and even undetectable.

Typical Properties

Property	Unit	Method	Value
API Gravity	-	ASTM D4052	51.0
Specific Gravity @15.6°C/15.6°C [60°F/60°F]	-	ASTM D4052	0.775
Density @15.6°C [60°F]	kg/L	ASTM D4052	0.775
Density @15.6°C [60°F]	lb/gal	ASTM D4052	6.46
Density @15°C	kg/m ³	ASTM D4052	775
Coefficient of Cubic Expansion @20°C	10 ⁻⁴ /°C	Calculated	9
Refractive Index @20°C	-	ASTM D1218	1.433
Colour	Saybolt	ASTM D156	+30
Copper Corrosion (1hr @ 100°C)	-	ASTM D130	1a
Distillation, Initial Boiling Point	°C	ASTM D86	253
Distillation, Final Boiling Point	°C	ASTM D86	270
Relative Evaporation Rate (nBUAc=1)	-	ASTM D3539	< 0.01
Relative Evaporation Rate (Ether=1)	-	DIN 53170	> 3900
Antoine Constant A #	kPa, °C	-	5.73697
Antoine Constant B #	kPa, °C	-	1486.73
Antoine Constant C #	kPa, °C	-	138.560

Antoine Constant: Temperature range	°C	-	+95 to +260
Vapor Pressure @20°C	kPa	Calculated	< 0.01
Vapor Pressure @50°C	kPa	Calculated	< 0.01
Saturated Vapor Concentration @20°C	g/m ³	Calculated	0.9
Volatile Organic Compound (VOC)	g/L	EU / EPA	775
Paraffins	% m/m	GC	98
Naphthenes	% m/m	GC	2
Aromatics	mg/kg	SMS2728	< 100
Benzene	mg/kg	GC	< 1
Sulfur	mg/kg	ISO 20846	< 0.5
Flash Point	°C	ASTM D93	110
Lower Explosion Limit in Air	% v/v		0.5
Upper Explosion Limit in Air	% v/v		7.0
Auto Ignition Temperature	°C	ASTM E659	> 200
Electrical Conductivity @25°C	pS/m	IEC 60247	< 0.1
Electrical Constant @25°C	-	IEC 60247	2.05
Aniline Point	°C	ASTM D611	92
Kauri-Butanol Value	-	ASTM D1133	20
Pour Point	°C	ASTM D97	-27
Hildebrand Solubility Parameter	(cal/cm ³) ^{1/2}	-	7.5
Hydrogen Bonding Index	-	-	0
Fractional Polarity	-	-	0
Surface Tension @20°C	mN/m	-	27
Viscosity @25°C	mm ² /s	ASTM D445	3.2
Viscosity @40°C	mm ² /s	ASTM D445	2.3
Molecular Weight	g/mol	Calculated	210

Test Methods

Copies of copyrighted test methods can be obtained from the issuing organisations:



American Society for Testing and Materials (ASTM)
International Electrotechnical Commission (IEC)
International Organisation for Standardization (ISO)
Deutsches Institut für Normung (DIN)

www.astm.org
www.iec.ch
www.iso.org
www.din.de

MasimoSol series (SMS) methods are issued by Masimo Chemicals South Africa (Pty) Ltd. Requests for copies of SMS can be made through Masimo Chemicals South Africa (Pty) Ltd.

N.B: For routine quality control local test methods may be applied. Such methods have been validated against those mentioned in this datasheet.

Quality

MasimoSol GTL GS 250 does not contain detectable quantities of heavy metals and chlorinated compounds.

Hazard Information

For detailed Hazard Information please refer to Safety Data Sheet, which can be requested through Masimo Chemicals South Africa (Pty) Ltd.

Storage Handling

Provided proper storage and handling precautions are taken we should expect MasimoSol GTL GS 250 to be technically stable for at least 12 months. For detailed advice on Storage and Handling please refer to Masimo Chemicals South Africa (Pty) Ltd.

Trademark

MasimoSol is a Masimo Chemicals South Africa (Pty) Ltd trademark.

Warranty/Disclaimer

All products purchased or supplied by Masimo Chemicals companies are subject to the terms and conditions set out in the contract, order confirmation and/or bill of lading. All other information supplied by Masimo Chemicals companies, including that herein, is considered accurate but is furnished upon the express condition that the customer shall make its own assessment to determine a product's suitability for a particular purpose. Except as may be set forth in the applicable contract, order confirmation and/or bill of lading, Masimo Chemicals companies make no warranty, express or implied, including regarding any information supplied or the data upon which it is based on the results to be obtained from the use of such products or information, or concerning product, whether of satisfactory quality, merchantability, fitness for any particular purpose or otherwise, or with respect to intellectual property infringement as a result of use of information or products, and none shall be implied.